

THIXOTROPIC EPOXY RESIN AND CYCLOALIPHATIC AMINES-BASED SYSTEM

DESCRIPTION

ULK K-050 is fully featured among the latest epoxy generation with exceptional physical and chemical characteristics. It can be used on either light or white stones due to its remarkable UV and yellowing resistance. Easy colouring for use on dark and coloured stones. Suitable for vertical joints; minimal shrinkage during hardening process and excellent fatigue resistance. Recommended for bonding and outdoors applications due to its high weather resistance.

INSTRUCTIONS FOR USE

The surface that has to be glued has to be clean and slightly rough before the application. mix component A with component B until obtaining a homogeneous blend. the mixture obtained must be used within 20-30 minutes. the surface will be walkable after 24 hours. the compound can not be used below 5° C and is suggests to observe the percentage between the two component A and B with 100:50 ratio. don't put the mixed product inside the jar.



TECHNICAL DATA -COMPONENT A

BASED SYSTEM	<i>thixotropic epoxy resin and cycloaliphatic amines</i>
COLOUR	Ice white
DENSITY	1.14 g/cm ³
FLASH POINT	> 150
PHR	100:50
SHELF LIFE	12 months

TECHNICAL DATA -COMPONENT B

BASED SYSTEM	<i>thixotropic epoxy resin and cycloaliphatic amines</i>
COLOUR	Ice white
ACTIVE CONTENT	100
AMINE VALUE	200-400 mg KOH/g
PHR	100:50
SHELF LIFE	12 months

Please note: the data in this sheet are based on our best experience and indicative only.

For the safety rules please have a look at our safety data sheet.

This sheet cannot be reproduced or changed in any of its parts without permission of Global Shipping S.p.a. Unipersonale.